



ONE BONTEX DRIVE  
 BUENA VISTA, VIRGINIA 24416-1500  
 TELEPHONE (540) 261-2181  
 FAX (540) 261-3784  
 email: [bontex@bontex.com](mailto:bontex@bontex.com)  
<http://www.bontex.com>



# **BONTEX® 244NRFFVB**

## **Visorboard**

### *Typical Properties*

BONTEX® 244 NRFFVB meets the required restrictions for hazardous substances.

BONTEX® -- Go with BONTEX® for High Performance

BONTEX® products are Mori-Fresh® treated to retard growth of bacteria, fungi, and mold.

BONTEX® products are produced with primary and secondary fibers, a sustainable resource.

TEST		2.45 mm	TEST METHOD	UNITS
<b>Stiffness</b>	<b>MD CMD</b>	4500 2300 - 2700	<b>TAPPI T489</b>	Taber
<b>Transverse Tensile Z (Dry)</b>		5	<b>*SATRA TM80</b>	Kg/cm <sup>2</sup>
<b>% Moisture</b>		1.5	<b>TAPPI T412</b>	%
<b>Elmendorf Tear</b>	<b>MD CMD</b>	3000 4500	<b>TAPPI T414</b>	Grams

The data listed are typical or average values or engineering estimates, based on tests conducted by independent laboratories or by the manufacturer. They are indicative only of the results obtained in such tests and should not be considered as guaranteed maximum or minimums. Materials must be tested under actual service to determine their suitability for a particular purpose.

\*Signifies SATRA Laboratory Accredited Test Procedures