



ONE BONTEX DRIVE  
 BUENA VISTA, VIRGINIA 24416-1500  
 TELEPHONE (540) 261-2181  
 FAX (540) 261-3784  
 email: bontex@bontex.com  
<http://www.bontex.com>



# BONTEX® 244 W

## *Typical Properties*

BONTEX® 244 W meets the required restrictions for hazardous substances.

BONTEX® -- Go with BONTEX® for High Performance.

BONTEX® products are Mori-Fresh® treated to retard growth of bacteria, fungi, and mold.

BONTEX® products are produced with primary and secondary fibers, a sustainable resource.

TEST	1.00 mm	1.25 mm	1.50 mm	1.75 mm	2.00 mm	TEST METHOD	UNITS
Stiffness MD	715	910	1150	1325	1510	TAPPI T489	Taber
Stiffness CD	345	435	515	605	735	TAPPI T489	Taber
Transverse Tensile Z (Dry)	3	3	4	5	5	*SATRA TM80	Kg/cm <sup>2</sup>
Tensile MD	29	34	40	44	50	SATRA TM2	Kg/cm
Tensile CD	13	17	20	22	25	SATRA TM2	Kg/cm
Rib Shear	>40	>40	>40	>40	>40	*SATRA TM405	Kg / 2.54 cm

The data listed are typical or average values or engineering estimates, based on tests conducted by independent laboratories or by the manufacturer. They are indicative only of the results obtained in such tests and should not be considered as guaranteed maximum or minimums. Materials must be tested under actual service to determine their suitability for a particular purpose.

\*Signifies SATRA Laboratory Accredited Test Procedures