



ONE BONTEX DRIVE
 BUENA VISTA, VIRGINIA 24416-1500
 TELEPHONE (540) 261-2181
 FAX (540) 261-3784
 email: bontex@bontex.com
<http://www.bontex.com>

Confidential



BONTEX® 347 FF Enviro-Insole

Typical Properties

BONTEX® 347 FF meets the required restrictions for hazardous substances.

BONTEX® -- Go with BONTEX® for High Performance.

BONTEX® products are Mori-Fresh® treated to retard growth of bacteria, fungi, and mold.

BONTEX® products are produced with primary and secondary fibers, a sustainable resource.

TEST	.90 mm	1.00 mm	1.25 mm	1.50 mm	1.75 mm	2.00 mm	TEST METHOD	UNITS
Stiffness MD CD	380 135	420 150	890 380	1490 750	2100 1050	2900 1450	TAPPI T489	Taber
Transverse Tensile (Z) Dry	3.0	3.0	3.0	3.0	3.0	3.0	*SATRA TM80	Kg/cm ²
Ross Flex CD	25,000 + No Cracking	25,000 + No Cracking	25,000 + No Cracking	20,000 + No Cracking	10,000 + No Cracking	10,000 + No Cracking	ASTM D 1052-05	Cycles

The data listed are typical or average values or engineering estimates, based on tests conducted by independent laboratories or by the manufacturer. They are indicative only of the results obtained in such tests and should not be considered as guaranteed maximum or minimums. Materials must be tested under actual service to determine their suitability for a particular purpose

Quality Assurance Coordinator

06-16-08

*Signifies SATRA Laboratory Accredited Test Procedures