



ONE BONTEX DRIVE  
 BUENA VISTA, VIRGINIA 24416-1500  
 TELEPHONE (540) 261-2181  
 FAX (540) 261-3784  
 email: [bontex@bontex.com](mailto:bontex@bontex.com)  
<http://www.bontex.com>



# BONTEX® 47 FF/T

## *Typical Properties*

BONTEX® 47 FFT meets the required restrictions for hazardous substances

BONTEX® -- Go with BONTEX® for High Performance.

BONTEX® products are Mori-Fresh® treated to retard growth of bacteria, fungi, and mold.

BONTEX® products are produced with primary and secondary fibers, a sustainable resource.

TEST	.90 mm	.100 mm	1.25 mm	TEST METHOD	UNITS
<b>Stiffness MD</b>	550	635	920	<b>TAPPI T489</b>	Taber
<b>Stiffness CD</b>	275	315	440	<b>TAPPI T489</b>	Taber
<b>Transverse Tensile Z (Dry)</b>	5.0	5.0	5.0	<b>*SATRA TM80</b>	Kg/cm <sup>2</sup>
<b>Ross Flex</b>	50,000	50,000	50,000	<b>*SATRA TM60</b>	Cycles

The data listed are typical or average values or engineering estimates, based on tests conducted by independent laboratories or by the manufacturer. They are indicative only of the results obtained in such tests and should not be considered as guaranteed maximum or minimums. Materials must be tested under actual service to determine their suitability for a particular purpose.

\*Signifies SATRA Laboratory Accredited Test Procedures