



ONE BONTEX DRIVE
 BUENA VISTA, VIRGINIA 24416-1500
 TELEPHONE (540) 261-2181
 FAX (540) 261-3784
 email: bontex@bontex.com
<http://www.bontex.com>



Certificate No.1203010
 Standard Issue 2000

BONTEX® 48

Typical Properties

BONTEX® 48 meets the required restrictions for hazardous substances.

BONTEX® -- Go with BONTEX® for High Performance.

BONTEX® products are Mori-Fresh® treated to retard growth of bacteria, fungi, and mold.

BONTEX® products are produced with primary and secondary fibers, a sustainable resource.

TEST	.30 mm	.50 mm	.75 mm	1.00 mm	1.25 mm	1.50 mm	TEST METHOD	UNITS
Density	.60	.60	.60	.60	.60	.60	SATRA TM12	g/cm ³
Stiffness MD	25	65	280	510	870	1240	TAPPI T489	Taber
CMD	15	30	95	205	410	620		
Tensile MD	6	10	14	19	24	19	SATRA TM2	Kg/cm
CMD	3	5	8	11	14	17		
Tear Strength	1000	1100	1300	1500	1700	2000	TAPPI T414	Grams
SATRA- Flex CMD	200	700	900	1200	1500	1700	*SATRA TM3	Cycles

The data listed are typical or average values or engineering estimates, based on tests conducted by independent laboratories or by the manufacturer. They are indicative only of the results obtained in such tests and should not be considered as guaranteed maximum or minimums. Materials must be tested under actual service to determine their suitability for a particular purpose.

*Signifies SATRA Laboratory Accredited Test Procedures