



ONE BONTEX DRIVE
 BUENA VISTA, VIRGINIA 24416-1500
 TELEPHONE (540) 261-2181
 FAX (540) 261-3784
 email: bontex@bontex.com
<http://www.bontex.com>



Certificate No.1203010
 Standard Issue 2000

BONTEX® 90G

Typical Properties

BONTEX® 90 G meets the required restrictions for hazardous substances.

BONTEX® -- Go with BONTEX® for High Performance

BONTEX® products are Mori-Fresh® treated to retard growth of bacteria, fungi, and mold.

BONTEX® products are produced with primary and secondary fibers, a sustainable resource.

The data listed are typical or average values or engineering estimates, based on tests conducted by independent laboratories or by the manufacturer. They are indicative only of the results obtained in such tests and should not be considered as guaranteed maximum or minimums. Materials must be tested under actual service to determine their suitability for a particular purpose.

*Signifies SATRA Laboratory Accredited Test Procedures

TEST	1.50 mm	1.70 mm	2.00 mm	2.25 mm	TEST METHOD	UNITS
Density	0.55	0.55	0.55	0.55	SATRA TM12	g/cm ³
Stiffness MD CMD	3975 1950	4500 2200	5000 3000	5600 3400	TAPPI T489	Taber
Dry Tensile MD CMD	27 16	39 20	48 27	56 31	SATRA TM2	Kg/cm
Dry Elongation MD CMD	4 6	4 6	4 6	4 6	SATRA TM2	%
Transverse Tensile Z (Dry)	3	3	5	5	*SATRA TM80	Kg/cm ²
Shore A Hardness	90-95	90-95	90-95	90-95	ASTM D 2240	
Water Absorption (8 hour) (Max)	40	40	40	40	*SATRA TM6	%
Water Desorption (16 hour) (Min)	80	80	80	80	*SATRA TM6	%